

Office of Intellectual Property Counsel  
3M Innovative Properties Company  
PO Box 33427  
St. Paul, Minnesota 55133-3427  
651/733 1500

**PATENT**

Docket No.

54565USA4A

**Transmittal of Patent Application - Rule 1.53(b)**

Box: Patent Application  
Assistant Commissioner for Patents  
Washington, D.C. 20231

Inventor(s): Mark F. Schulz and Omar Farooq  
Title: MACROPOROUS INK RECEIVING MEDIA

1. ☒ Enclosed is the above-mentioned new patent application. It includes -0- sheet(s) of drawings.
2. ☒ Enclosed is an executed declaration or oath.
3. ☒ Enclosed are an application assignment to 3M Innovative Properties Company and a completed Assignment Recordation Cover Sheet.
4. ☐ Enclosed is a Certified Copy of Priority Document(s) \_\_\_\_\_ (if foreign priority is claimed).
5. ☐ Enclosed is \_\_\_\_\_.
6. ☒ The fee for filing the application is computed as follows:

Claims As Filed					
(1) For	(2) Number Filed	(3) Number Extra	(4) Rate	(5) Basic Fee	
Total Claims	21 -20 =	1	x \$18.	\$760.	
Independent Claims	4 -3 =	1	x \$78.	\$ 78.00	
Additional fee for filing one or more multiple dependent claims			\$260.	\$	
Total amount due →				\$ 856.00	

7. ☒ Please charge to Deposit Account 13-3723 any fees under 37 CFR 1.16 and 1.17 which may be required to file and during the entire pendency of this application. This authorization includes the fee for any extension of time under 37 CFR 1.136(a) that may be necessary. To the extent any such extension should become necessary it is hereby requested. A copy of this transmittal letter for fee processing is enclosed.
8. ☒ Enclosed is a return receipt postcard

Respectfully submitted

Registration Number	Telephone Number
39,594	651/736-6935
Date	
May 18, 1999	

Signature
<i>Scott A. Bardell</i>
Print Name
Scott A. Bardell

**Certificate of Express Mailing**

Pursuant to 37 CFR 1.10 I certify that this application is being deposited on the date indicated below with the United States Postal Service "Express Mail Post Office to Addressee" service addressed to: Assistant Commissioner for Patents, Washington, D.C. 20231.

Express Mail Mailing Label No.

EL122725914US

Date of Deposit

May 18, 1999

Signature of Person Mailing Application

*Kathleen M. Goers*

Printed Name of Person Mailing Application

Kathleen M. Goers

MACROPOROUS INK RECEIVING MEDIA

Field of the Invention

This invention relates to macroporous ink receiving media that provide durable high quality images with pigmented inks deposited thereon.

Background of the Invention

Inkjet and spray jet printing using dye-based inks is one method of manufacturing printed porous substrates such as textiles. Printed dyes may be "fixed" with dye mordants to improve waterfastness. Inkjet printing is well-suited for, among other things, short printing run and high resolution applications.

Pigment-based inks are commonly applied to porous substrates such as textiles by screen-printing methods, and are typically more durable than dye-based inks. In order to retain the pigment on the textile, a binder resin is employed to provide a means for anchoring the pigment to the textile. Screen-printing inks have viscosities that far exceed the maximum viscosities that may be successfully printed by inkjet methods. Additionally, the binder resins used in screen inks generally lend a stiffer (i.e., aesthetically undesirable) hand to the textile than if the same textile had been dyed. Screen printing is not a technology well-suited to short run printing in that a considerable effort is required to change screens and/or ink colors.

Dye-based inks generally suffer from poor stability compared to pigment-based inks, especially when lightfastness and waterfastness are considered.

There exists a need to provide durable lightfast and waterfast articles that combine the advantages of lightfastness, waterfastness, soft hand, and high resolution.

Summary of the Invention

One aspect of the present invention is an ink receiving medium comprising a macroporous substrate having a pigment management system and a fluid management system in contact with surfaces of macropores of the substrate therein.

Another aspect of the present invention is an ink receiving medium comprising a macroporous substrate impregnated with a composition comprising one or more water-soluble multivalent metal salts together with a surfactant or a combination of surfactants for the ink and substrate being employed.

Another aspect of the present invention is an ink receiving medium comprising a macroporous substrate having a pigment management system and an optional fluid management system wherein the pigment management system is a non-aqueous solvent soluble metal salt.

The novel ink receiving media when imaged using an inkjet printer provide durable, high color intensity and high quality images which are tack-free and rapidly dry to the touch.

In another aspect, the present invention provides an ink receiving medium/ink set comprising a macroporous substrate impregnated with one or more multivalent water-soluble metal salts and a surfactant or combination of surfactants, and an ink that contains pigment colorants.

The ink receiving media of the invention provide images having improved durability, waterfastness, smear resistance, rapid dry times, and long term durability using a macroporous substrate without absorptive polymeric binders, or additional processes such as UV exposure or heating.

In a preferred embodiment, the ink colorant is a pigment dispersion having a dispersant bound to the pigment that will destabilize, flocculate, agglomerate, or coagulate on contact with the ink receiving medium. Upon deposition of ink at or just below the surface of the macroporous substrate, the fluid management system wicks the ink into the fibers or macropores where the pigment management system fixes (i.e., immobilizes) the pigment.

A feature of the present invention is the ability to "fine tune" the properties of the ink receiving media of the present invention to deal with the variables of inkjet ink delivery, including without limitation: drop volume, ink surface tension, porosity of the ink receiving medium, and capacity of the ink receiving medium to receive ink.

Other features of ink receiving media of the invention include that they: are cost competitive, work with pigmented inks, have high resolution, have high color density, provide wide color gamut, are waterfast, are smudge resistant, and provide rapid drying.

An advantage of ink receiving media of the present invention is that a laminated protective cover layer is not necessary to achieve water resistant images.

Another advantage of ink receiving media of the present invention is the ability to use inexpensive readily available materials in printing processes to produce images on, for example, custom papers such as real or simulated ragstock, textile fabrics, spunbonded fiber media, melt-blown microfiber (i.e., BMF) media, polyethylene envelope mailers and the like.

Another advantage of ink receiving media of the present invention is very fast drying of the pigment and fluid management systems during coating or impregnation. The process saves significant amounts of energy and thus, reduces costs.

As used herein, a "macroporous substrate" means a substrate having an average pore size of from about 3  $\mu\text{m}$  up to about 5 millimeters, preferably from about 10  $\mu\text{m}$  to about 2 millimeters, more preferably from about 100  $\mu\text{m}$  to about 0.5 millimeter and does not include microporous films and particles. In addition, the macroporous substrates of the invention are characterized by having a solidity of from at least about 1 percent up to about 90 percent, preferably from at least about 5 percent to about 70 percent, and even more preferably from at least about 10 percent up to about 50 percent.

As used herein, a "pigment management system" means a composition comprising a metal salt that has coated or impregnated a substrate to prepare an ink receiving medium suitable for use in the process of inkjet printing.

As used herein, a "fluid management system" means a composition comprising at least one surfactant that has coated or impregnated a substrate to prepare an ink receiving medium suitable for use in the process of inkjet printing.

The term "arithmetic median fiber diameter" means the fiber diameter for which equal numbers of fibers have diameters that lie above or below this value. The arithmetic median fiber diameter can be determined through microscopic examination.

The term "solidity" means the volume of fibers per volume of web. It is a unitless fraction typically represented by  $\alpha$ :

$$\alpha = \frac{m_f}{P_f L_f}$$

where  $m_f$  is the fiber mass per sample surface area;  $P_f$  is the fiber density; and  $L_f$  is the macroporous substrate thickness. Solidity is used herein to refer to the macroporous substrate itself and not to any composite structure in which it may be included as a component thereof. When a macroporous substrate contains mixtures of two or more kinds of fibers, the individual solidities are determined for each kind of fiber using the same  $L_f$ . The individual solidities are added together to obtain the web's solidity,  $\alpha_w$ .

The term "average pore size" (also known as average pore diameter) is related to the arithmetic median fiber diameter and web solidity and can be determined by the following formula:

$$D = d_f \left\{ \left( \frac{2\alpha_w}{\pi} \right)^{-1/2} - 1 \right\}$$

where  $D$  is the average pore size,  $d_f$  is the arithmetic median fiber diameter, and  $\alpha_w$  is the web solidity.

#### Detailed Description of the Invention

Macroporous substrates useful in the present invention include but are not limited to woven or nonwoven fabrics of natural fibers such as cotton, flax, hemp, wood pulp, ramie, burlap, wool, silk, etc.; synthetic fibers such as rayon, acrylic, polyolefin fibers such as polypropylene, polyethylene, or polyvinyl chloride; polystyrene and block copolymers thereof with butadiene such as those sold under the trade designation KRATON; polyester fibers such as polycaprolactone or polyethylene terephthalate fibers, and fibers sold under the trade designation DACRON; polyamide fibers such as polycaprolactam and polyhexamethylenedipamide, (particularly including polyamide fibers sold under the trade designation NYLON); polyarylsulfones, poly(vinyl alcohol), poly(ethylene vinyl acetate), polyacrylates such as polymethyl methacrylate; polycarbonates; cellulosic polymers such as cellulose acetate butyrate; polyimides; polyurethanes, particularly including polyether polyurethanes; or blends thereof such as for example, rayon/polyester blends, polypropylene/polyethylene blends,

polypropylene/polyethylene terephthalate blends, polypropylene/polyamide blends, or any combination thereof. The fibers may range in size from 0.01 to 50 denier (denier is the weight in grams of a fiber 9000 meters in length) or more and may be present as individual fibers or twisted into yarns.

5 Useful macroporous substrates also include virtually any type of melt-blown or spunbonded fibrous substrates and pulp or paper materials having the desirable mechanical strength and integrity.

Macroporous substrates of the invention can be of unlimited length, depending on the size of the roll that can be easily handled. Usually, commercial quantities of the macroporous substrate for feeding into a commercial printer can be a roll having a length in excess of 10 meters, and preferably in excess of 20 meters and may be as long as several kilometers. The macroporous substrate can have a width ranging from about 0.03 meters to about 10 meters or more.

15 The porosity, average pore size, surface energy, and caliper of the macroporous substrate can be selected to provide suitable fluid management for the image graphic. Therefore, depending upon the pigmented ink selected for imaging, the type of ink can determine the type of porous surface most suitable for wicking of fluid from the deposited image graphic into the pore volume of the substrate. However, according to the present invention, a wide latitude in porosity is generally acceptable.

20 Sometimes, the chemical and physical properties (e.g., surface energy) of the porous surface requires assistance from surfactants to aid in the management of ink fluids. Therefore, a fluid management system containing at least one surfactant may be advantageously impregnated into the pore volume of the macroporous substrate. Application of the fluid management system may be performed as a separate and distinct step, or combined with the pigment management system and coated onto the substrate in a single step, followed by removal of any water and/or organic solvent or solvents, to provide particularly suitable surfaces for the particular fluid components of the pigmented inkjet inks. Surfactants can be cationic, anionic, nonionic, or zwitterionic. Many of each type of surfactant are widely available to one skilled in the art. Accordingly, any surfactant or combination of surfactants or less preferably, polymer(s) that will render said substrate hydrophilic, could be employed.

These may include but are not limited to fluorochemical, silicone and hydrocarbon-based surfactants wherein the said surfactants may be anionic or non-ionic. Furthermore, the non-ionic surfactant may be used either as it is or in combination with another anionic surfactant in water and/or organic solvent or solvents, said organic solvent being selected from the group consisting of alcohols, ethers, amides, ketones, and the like.

Various types of non-ionic surfactants can be used, including but not limited to: ZONYL fluorocarbons (e.g., ZONYL FSO, available from E.I. du Pont de Nemours and Co. of Wilmington, DE); FLUORAD FC- 170 or 171 surfactants (available from Minnesota Mining and Manufacturing Company (3M) of St. Paul, MN); PLURONIC block copolymers of ethylene and propylene oxide to an ethylene glycol base (available from BASF Corp. Chemicals Division of Mount Olive, NJ); TWEEN polyoxyethylene sorbitan fatty acid esters (available from ICI Americas, Inc. of Wilmington, DE); TRITON X series octylphenoxy polyethoxy ethanol (available from Rohm and Haas Co. of Philadelphia, PA); SURFYNOL tetramethyl decynediol (available from Air Products and Chemicals, Inc. of Allentown, PA); and SILWET L-7614 and L-7607 silicon surfactants (available from Union Carbide Corp. of Danbury, CT), and the like known to those skilled in the art.

Useful anionic surfactants include, but are not limited to, alkali metal and (alkyl)ammonium salts of: 1) alkyl sulfates and sulfonates such as sodium dodecyl sulfate and potassium dodecanesulfonate; 2) sulfates of polyethoxylated derivatives of straight or branched chain aliphatic alcohols and carboxylic acids; 3) alkylbenzene or alkylnaphthalene sulfonates and sulfates such as sodium laurylbenzene-sulfonate; 4) ethoxylated and polyethoxylated alkyl and aralkyl alcohol carboxylates; 5) glycinate such as alkyl sarcosinates and alkyl glycinate; 6) sulfosuccinates including dialkyl sulfosuccinates; 7) isethionate derivatives; 8) N-acyltaurine derivatives such as sodium N-methyl-N-oleyltaurate; 9) amphoteric alkyl carboxylates such as amphoteric propionates and alkyl and aryl betaines, optionally substituted with oxygen, nitrogen and/or sulfur atoms; and 10) alkyl phosphate mono or di-esters such as ethoxylated dodecyl alcohol phosphate ester, sodium salt.

Useful cationic surfactants include alkylammonium salts having the formula  $C_nH_{2n+1}N(CH_3)_3X$ , where X is OH, Cl, Br,  $HSO_4$  or a combination of OH and Cl, and

where n is an integer from 8 to 22, and the formula  $C_nH_{2n+1}N(C_2H_5)_3X$ , where n is an integer from 12 to 18; gemini surfactants, for example those having the formula:  $[C_{16}H_{33}N(CH_3)_2C_mH_{2m+1}]X$ , wherein m is an integer from 2 to 12 and X is as defined above; aralkylammonium salts such as, for example, benzalkonium salts; and  
5 cetylthylpiperidinium salts, for example,  $C_{16}H_{33}N(C_2H_5)(C_5H_{10})X$ , wherein X is as defined above.

The macroporous ink receiving media of the invention have a pigment management system prepared by addition of a solution containing at least one multivalent metal salt into the pore volume of the macroporous substrate and removal of the solvent.  
10 The multivalent metal salts are believed to serve as reagents to rapidly destabilize dispersants surrounding the pigment particles in the ink, whereby the pigment particles coagulate or flocculate as the remainder of the ink fluid continues through pores and along the surfaces of the ink receiving medium. The multivalent salts therefore provide a chemical means of pigment management along surfaces of the pores. The salts coat the surfaces of the macroporous substrate and, once dried, are resistant to physical removal. The metal salts are soluble in water for both preparing solutions and during imaging, but not after complexing with the dispersing aid that surrounds the pigment particles in the ink (i.e., the printed image is waterfast).

Non-limiting examples of multivalent metal salts useful in the present invention include the metal cations from Group IIA and above in the Periodic Table, such as Ca, Mg, Ti, Zr, Fe, Cu, Zn, Ta, Al, Ga, Sn, with counter ions such as sulfate, nitrate, bisulfate, chloride; aromatic carboxylates such as benzoates, naphthalates, phthalates, etc.; sulfocarboxylates, sulfophthalates, and the like.

Specific examples of preferred multivalent metal salts include aluminum sulfate, aluminum nitrate, gallium nitrate, ferrous sulfate, chromium sulfate, zirconium sulfate, magnesium sulfophthalate, copper sulfophthalate, zirconium sulfophthalate, zirconium phthalate, zinc sulfate, zinc acetate, zinc chloride, calcium chloride, calcium bromide, magnesium sulfate, magnesium chloride, aluminum sulfophthalate, aluminum sulfoisophthalate, and combinations thereof. These compounds are typically sold and can  
30 be used in the hydrated form. Of the various possible salts, aluminum sulfate and



aluminum sulfophthalate are presently preferred.

The amount of salts that can be used in the coating solution for imbibing in the porous substrate of the present invention can range from about 0.1 weight percent to about 50 weight percent, and preferably from about 0.5 weight percent to about 20 weight percent.

The amount of surfactant that can be used in the coating solution for imbibing in the porous substrate of the present invention can range from about 0.01 weight percent to about 10 weight percent, and preferably from about 0.1 weight percent to about 5 weight percent.

Optionally, heat or ultraviolet light stabilizers can be used in ink receptors of the present invention. Non-limiting examples of such additives include TINUVIN 123 or 622LD, or CHIMASSORB 944 (hindered amine light stabilizers, available from Ciba Specialty Chemicals Corp. of Tarrytown, NY), and UVINUL 3008 (available from BASF Corporation Chemicals Division of Mount Olive, NJ). Such stabilizers can be present in a coating solution to be impregnated into the macroporous substrate in the range from about 0.2 weight percent to about 20 weight percent. Preferably, the stabilizer is present in an amount from about 0.1 to about 10 weight percent, more preferably in an amount of from about 0.5 to about 5 weight percent.

Optionally, ultraviolet light absorbers can be used in ink receiving media of the present invention. Non-limiting examples of such absorbers include TINUVIN II 30 or 326 (available from Ciba Specialty Chemicals Corp.), UVINUL 40501 1 (available from BASF Corporation), and SANDUVOR VSU or 3035 (available from Sandoz Chemicals of Charlotte, NC). Such absorbers can be present in the coating solution and can range from about 0.01 weight percent to about 20 weight percent. Preferably, the absorber is present in an amount from about 1 to about 10 weight percent.

Optionally, anti-oxidants can be used in ink receiving media of the present invention. Non-limiting examples of such anti-oxidants include IRGANOX 1010 or 1076 (available from Ciba Specialty Chemicals Corp.), UVINUL 2003 AD (available from BASF Corporation Chemicals Division).

Such anti-oxidants can be present in the coating solution and can range from about 0.2 weight percent to about 20 weight percent. Preferably, the anti-oxidant is present in an

amount from about 0.4 to about 10 weight percent, and more preferably in an amount from about 0.5 to about 5 weight percent.

Optionally, opacifying pigments can be used in ink receiving media of the present invention. Non-limiting examples of such opacifying pigments include titanium dioxide pigments, barium sulfate pigments, and the like. Such opacifying pigments can be present in the coating solution and can range from about 0.01 weight percent to about 50 weight percent. Preferably, the opacifying pigment is present in an amount from about 1 to about 30 weight percent.

Optionally, organic binders can be used in the ink receiving media of the invention. The organic binders are used to bind opacifying pigments and/or other additives onto the macroporous substrate. Preferably, the organic binders are soluble or dispersible in water so that they may be easily incorporated into the compositions used to coat macroporous substrates in forming the ink receiving media of the invention. Non-limiting examples of such organic binders include acrylic emulsions, styrene-acrylic emulsions, polyvinylalcohol and the like. Such organic binders can be present in the coating solution from about 0.1 to about 50 weight percent, preferably about 1 to about 30 weight percent based on total weight of the coating solution, including surfactants and metal salts, with the remainder being water and/or organic solvent.

An ink receiving medium of the present invention has two major opposing surfaces and can be employed for printing (for example, by inkjet methods) on both surfaces. Optionally, one of the major surfaces can be dedicated for the purpose of adhering the finished image graphic to a supporting surface such as a wall, a floor, or a ceiling of a building, a sidewall of a truck, a billboard, or any other location where an excellent quality image graphic can be displayed for education, entertainment, or information.

Minnesota Mining and Manufacturing Company (3M) offers a variety of image graphic receptor media and has developed an array of pressure-sensitive adhesive formulations that can be employed on the major surface opposing the surface intended for imaging. Among these adhesives are those disclosed in U.S. Patent Nos. 5,141,790 (Calhoun et al.); 5,229,207 (Paquette et al.); 5,800,919 (Peacock et al.); 5,296,277 (Wilson et al.); 5,362,516 (Wilson et al.); EPO Patent Publication EP 0 570 515 B1 (Steelman et al.), and co-pending, co-assigned U.S. Patent Application Serial Nos.

08/775,844 (Sher et al.) and 08/664,730 (Peloquin et al.).

Any of these adhesive surfaces should be protected by a release or storage liner such as those commercially available from Rexam Release of Bedford Park, IL. Alternatively to adhesives, mechanical fasteners can be used if laminated in some known  
5 manner to that opposing major surface of the receptor of the present invention. Non-limiting examples of mechanical fasteners include hook and loop, Velcro™, Scotchmate™ and Dual Lock™ fastening systems, as disclosed in published PCT Patent Application No. WO 98/39759 (Loncar), the disclosures of which are incorporated by reference herein.

While the imaging major surface is not covered before imaging, after imaging, an  
10 optional layer may be applied to that imaged surface of the ink receiving medium to protect and enhance the image quality of the image on the receptor. Non-limiting examples of optional layers are overlaminates and protective clear coatings commercially available from Minnesota Mining and Manufacturing Company (3M) from its Commercial Graphics Division and those disclosed in U.S. Patent No. 5,681,660 (Bull et al.), the  
15 disclosure of which is incorporated by reference herein. Other products known to those skilled in the art can also be used.

The invention in its preferred mode is made by impregnation of the macroporous substrate with a pigment management system composition (i.e., a solution containing one or more multivalent metal salts) and with a suitable fluid management system (i.e., one or more surfactants) as required followed by drying at a temperature of about 100 to about  
20 120 °C. After the receptor is dried, it can be imaged using conventional inkjet imaging techniques embodied in commercially available printers.

Impregnation of the pigment management system and/or fluid management system may be accomplished by dissolving or mixing the salt and/or surfactant in de-ionized  
25 water or a mixture of an alcohol and de-ionized water. Impregnation of the solution may be done using conventional equipment and techniques such as slot fed knife, rotogravure devices, padding operations, dipping, spraying, and the like. It is preferred that the pigment management system fills the pores of the substrate without leaving substantial quantities on the surface. Excessive amounts of solids could plug the pores and in turn  
30 causes smearing and slow dry times during imaging. Coating weights depend on porosity, thickness, and chemical nature of the substrate, but may be readily determined by routine

0331034-05159  
5 optimization. Typical wet coating weights are from about 1 up to about 500 grams per square meter, preferably from about 10 up to about 50 grams per square meter, more preferably from about 15 to about 30 grams per square meter. Optional additives may be added before, during, or after impregnation of the pigment management system and/or fluid management system.

The printing industry has previously employed dye-based inks, although pigment-based inks are becoming more prevalent. Use of pigment colorants is preferred over dye colorants because of durability and ultraviolet light stability in outdoor applications.

10 Further, reference to ink with respect to this invention concerns aqueous-based inks, not solvent-based inks. Aqueous-based inks are currently preferred in the printing industry for environmental and health reasons, among other reasons.

Minnesota Mining and Manufacturing Company (3M) produces a number of excellent pigmented inkjet inks for thermal inkjet printers. Among these products are Series 8551, 8552, 8553, and 8554 pigmented inkjet inks. The use of four principal colors: cyan, magenta, yellow, and black permit the formation of as many as 256 colors or more in the digital image. Further, pigmented inkjet inks, and components for them, are also produced by others, including Hewlett-Packard Corp. of Palo Alto, CA and E.I. du Pont de Nemours and Co., and a number of other companies that can be located at many commercial trade shows dedicated to the imaging and signage industries.

25 The ink receiving media of the present invention are highly fluid absorptive media. Some of the macroporous receptors are opaque because of their inherent light scattering ability while some are light transmissive. Using opaque backing support, the receptor can be used for reflective mode applications. The ink receiving media of the invention can be used as banners, signage, murals, art media, gallery display, trade show display, and the like. Because they are substantially waterfast, the receptor media of the invention can be used outdoors as well as indoors.

30 When the ink receiving media of the invention are imaged in DESIGN JET 2500 CP, DESIGN JET 3500 CP series (available from Hewlett-Packard Corp.) or Encad NOVAJET (available from Encad Inc. of San Diego, CA) wide-format printers using pigmented inks, it results in images with excellent quality with high color density which rapidly dry to the touch.

The advantages and unexpected results of the receptor media of the invention will now be demonstrated in the following examples.

### Examples

5 All of the amounts given are in weight percent unless otherwise stated. Unless otherwise stated, all of the components are available from Aldrich Chemical Co., Milwaukee, WI.

10 The wet rub test used in the examples was performed as follows: Water was placed on a portion of the printed image, and then rubbed with a thumb using light to moderate pressure. If the image did not smear, then the test was judged a pass. If smearing occurred, then the test was judged a fail.

As used in these examples, rapidly dry to the touch means that the image emerged from the printer sufficiently dry such that no ink transfer from the printed image occurred when contacted by a lightly applied dry finger.

15 The NOVAJET 4 wide format ink jet printer employed in the examples was obtained from Encad, Inc., using yellow, magenta, cyan, and black pigmented inks (Series 8551-8554, obtained from Minnesota Mining and Manufacturing Company (3M)).

20 The wide-format inkjet printers DESIGN JET 2500 CP and DESIGN JET 3500 CP were obtained from Hewlett-Packard Comp., Inc. and were used with yellow, magenta, cyan, and black pigmented inks (Cartridge Nos. C1892A, C1893A, C1894A, and/or C1895A, available from Hewlett-Packard).

ELEVES T0703WDO spunbonded polyethylene/polyester non-woven fabric (70 g/m<sup>2</sup> basis weight, 0.25 millimeter thickness), was obtained from Unitika Ltd. of Tokyo, Japan.

25 REEMAY 2033 spunbonded polyester (100 g/m<sup>2</sup> basis weight, 0.44 millimeter thickness), was obtained from Reemay, Inc. of Old Hickory, TN

Examples 1-5 and 10-13 use Composition A prepared by mixing the components described below in Table 1.

TABLE 1

Components	Weight Percent
Aluminum Sulfate, Hydrated	5.2
Diocetyl sulfosuccinate, sodium salt (DOS)	6.0
Isopropyl Alcohol	25.0
De-ionized Water	63.8

Example 1

A 30.5 centimeters x 25.4 centimeters piece of non-woven/fibrous polypropylene film (MIRACLOTH brand, available from Calbiochem, LaJolla, CA) was dipped into Composition A and then dried with a heat-gun (110 - 120 °C) for about 2 minutes. The dry fabric was laminated with a pressure-sensitive adhesive onto a transparent polyester sheet and then imaged using a NOVAJET 4 printer to obtain a bleed-free, feather-free, high density, and tack-free rapidly dry image. Imaging was accomplished using yellow, magenta, cyan, and black inks. On wet-rub, there was slight movement in the cyan color but no movement in any of the other colors. On dipping into water or subjecting the image to running water, there was no mobility of any color.

Comparative Example 1

A virgin non-woven polypropylene substrate was printed with the same image as described in Example 1. Comparative Example 1 showed an uneven image with high bleeding, feathering, and the image washed away when placed under running tap water.

Example 2

Example 2 was prepared as described in Example 1 above, except that the printable substrate was melt-blown non-woven polypropylene fabric, using 3505G polypropylene, available from Exxon Chemicals of Houston, TX, having an average fiber diameter of 7  $\mu\text{m}$  and a basis weight of 40  $\text{g/m}^2$  and a thickness of 0.54 millimeter to obtain an image with similar characteristics and properties, including waterfastness to those obtained in Example 1.

### Example 3

Example 3 was prepared as in Example 1 except that the printable substrate was non-woven polyester fabric made using a melt-blown process with polyethylene terephthalate resin (Mw 44,000; Mn 19,000), to make fibers having an average fiber diameter of 17  $\mu\text{m}$ , and a basis weight of 100  $\text{g}/\text{m}^2$  and the laminated substrate was spunbonded polyester. The laminated fabric was then impregnated with Composition A, dried with a heat-gun (110 - 120  $^{\circ}\text{C}$ ) for about 2 - 3 minutes and then imaged with a DESIGN JET 2500 CP printer to obtain a bleed-free, feather-free, tack-free, and rapidly dry image. On wet-rub, there was slight movement in the cyan but no movement in any of the other colors. On dipping into water or subjecting it to running water, there was no mobility of any of the color.

### Comparative Example 2

A non-coated non-woven blown microfiber polyester fabric was printed as described in Example 3 provided an image that washes away when exposed to running or stationary water.

### Example 4

This example demonstrates impregnation of aluminum sulfate compositions into a piece of woven polyester fabric, TX-1012 (Alpha-10, 100 percent continuous filament polyester, available from Texwipe Co. of Upper Saddle River, NJ). A piece of non-woven polyester fiber was dipped into Composition A (Table 1) and then was dried with a heat-gun as described in Example 3. The impregnated fabric was then laminated onto a spunbonded polyester (Unitika Ltd. of Tokyo, Japan) backing using a pressure-sensitive adhesive. When imaged using a DESIGN JET 2500 CP, DESIGN JET 3500 CP or NOVAJET 4 printer a bleed-free, feather-free, tack-free, high color density rapidly dry image with sharp and bright edges was obtained. On wet-rub, there was slight movement in the cyan color. On dipping into water or subjecting it to running water, there was no mobility of any color.

### Comparative Example 3

A non-coated piece of the fabric used in Example 4 was printed as described in Example 4 and provided an image that bled, feathered, and washed away when exposed to running or stationary water.

### Example 5

A piece of polyethylene spunbonded material (TYVEK™, E.I. du Pont de Nemours) was flood-coated with Composition A (Table 1) using a Mayer rod #4 (available from R & D Specialties, Inc. of Whittier, CA). The impregnated substrate was dried with a heat-gun as described in Example 4. The ink receiving medium provided good imaging and density, with some feathering and smudging when imaged with a NOVAJET 4 printer. The ink receiving medium provided good imaging and density, with some feathering when imaged in a DESIGN JET 2500 CP or DESIGN JET 3500 CP printer.

### Example 6

A spunbonded polyethylene/polyester non-woven fabric (ELEVES T0703WDO) was coated with a pigment management system containing 5 percent aluminum sulfate and 0.5 percent dioctyl sulfosuccinate, sodium salt (DOS) surfactant in water, followed by drying off the water in an oven at 100 °C. This substrate was printed using a DESIGN JET 2500 CP printer. The image exhibited high color density, no bleed or feathering between colors (i.e., sharp edges), and uniform coloration. Running the image under tap water did not noticeably remove any colorants. This image was soaked in water overnight without an appreciable change in the image quality.

### Comparative Example 4

A non-coated sample of spunbonded polyethylene/polyester non-woven fabric (ELEVES T0703WDO) was printed as in Example 6. The image showed relatively low color density, severe ink bleed, ink feathering between colors (i.e., non-sharp edges), and non-uniform coloration. When the non-coated substrate was run under tap water for about 1 second, the colorants were readily removed.



Comparative Example 5

A sample of spunbonded polyethylene/polyester non-woven fabric (ELEVES T0703WDO) was coated with a solution of 0.5 percent DOS surfactant in water, followed by drying off the water in an oven at 100 °C. This substrate was then printed as in Example 6. The image and waterfastness properties were similar to those observed in Comparative Example 4.

Example 7

An ink receiving medium was made as in Example 6, except spunbonded polyester (REEMAY 2033) was used as the non-woven fabric. The substrate was printed as in Example 6. Excellent image quality and waterfastness was provided as in Example 6.

Comparative Example 6

A non-coated sample of spunbonded polyester non-woven fabric (REEMAY 2033), was printed as in Example 7. The image showed relatively low color density, severe ink bleed, ink feathering between colors (i.e., non-sharp edges), and non-uniform coloration. When the non-coated substrate was run under tap water for about 1 second, the colorants were readily removed.

Comparative Example 7

A sample of spunbonded polyester non-woven fabric (REEMAY 2033) was coated with a solution of 0.5 percent DOS surfactant in water, followed by drying off the water in an oven at 100 °C. It was then printed as in Example 7. The image and waterfastness properties were similar to those observed in Comparative Example 6.

Example 8

An ink receiving medium was made as in Example 7, except that a pigment management system composition containing 0.5 percent aluminum sulfate and 0.5 percent DOS in water was used. The resulting image provided similarly excellent image quality and waterfastness as in Example 6.

#### Example 9

An ink receiving medium was made as in Example 6, except that a pigment management system composition containing 1.4 percent aluminum sulfate, 0.14 percent DOS, 22 percent TiO<sub>2</sub> pigment, and 25 percent (RHOPLEX™ B-60A, obtained from Rohm and Haas Co.) in water. The resulting image exhibited excellent image quality, waterfastness, and enhanced opacity for reflected viewing.

#### Example 10

A piece of paper (CASCADE X-9000, obtained from Boise Cascade Papers of Portland, OR) was flood-coated with Composition A (Table 1) using a Mayer rod #4 and was allowed to dry at room temperature. The paper receptor was then briefly dried with a heat-gun (110 - 120 °C) for about 1 minute. When imaged using a DESIGN JET 2500 CP printer, there was obtained a bleed-free, feather-free, rapidly dry image which showed some cockling. On wet-rub, there was some movement of all the colors. On dipping into water, there was no mobility of any of the color.

#### Example 11

Composition A (Table 1) was coated onto a thick artist's paper (coarse paper) to obtain cockle-free, high density, and high quality dry image with waterfastness as described in Example 10.

#### Example 12

Coating of Composition A (Table 1) was repeated onto a Whatman #54 filter paper by flood-coating procedure. The dry film when imaged using a NOVAJET 4 printer gave a cockle-free, high density, high quality, smudge-free, dry image, which was waterfast.

#### Example 13

Coating of Composition A (Table 1) was repeated in a piece of file-folder paper (thick, coarse off-white paper). The dry film when imaged using a NOVAJET 4 printer gave a cockle-free, high density, high quality, smudge-free, dry image that was waterfast.

What is Claimed is:

1. An ink receiving medium comprising:

5 a macroporous substrate having a fluid management system and having a pigment management system in contact with surfaces of macropores of the substrate therein.

2. The ink receiving medium according to claim 1 wherein the pigment management system comprises water-soluble multivalent metal salt.

10 3. The ink receiving medium according to claim 1 wherein the fluid management system comprises surfactant.

4. The ink receiving medium according to claim 1 wherein the macroporous substrate has an average pore size of from about 3 micrometers to about 5 millimeters.

5 5. The ink receiving medium according to claim 3 wherein said surfactant is non-ionic, cationic, anionic, or a combination of anionic and non-ionic surfactants.

20 6. The ink receiving medium according to claim 3 wherein said surfactant is selected from fluorochemical, silicone and hydrocarbon based surfactants, and combinations thereof.

25 7. The ink receiving medium according to claim 2 wherein the pigment management system further comprises an opacifying pigment.

30 8. The ink receiving medium according to claim 2 wherein said water-soluble multivalent metal salt is aluminum sulfate, aluminum nitrate, gallium nitrate, ferrous sulfate, chromium sulfate, zirconium sulfate, magnesium sulfophthalate, copper sulfophthalate, zirconium sulfophthalate, zirconium phthalate, zinc sulfate, zinc acetate,

zinc chloride, calcium chloride, calcium bromide, magnesium sulfate, magnesium chloride, aluminum sulfophthalate, aluminum sulfoisophthalate, or combinations thereof.

9. The ink receiving medium according to claim 1 wherein the fluid management system comprises surfactant and the surfactant is a hydrocarbon based anionic surfactant.

10. The ink receiving medium according to claim 9 wherein said surfactant comprises sodium salt of dioctyl sulfosuccinate.

11. The ink receiving medium according to claim 10 wherein the pigment management system comprises water-soluble multivalent salt and said salt comprises aluminum sulfate.

12. An ink receiving medium/ink set comprising a macroporous substrate impregnated with a composition comprising water-soluble multivalent salt and surfactant, and an ink that contains pigment colorants.

13. The ink receiving medium/ink set according to claim 12 wherein the macroporous substrate has an average pore size of from about 3 micrometers to about 5 millimeters.

14. The ink receiving medium/ink set according to claim 13 wherein the water-soluble multivalent metal salt is aluminum sulfate, aluminum nitrate, gallium nitrate, ferrous sulfate, chromium sulfate, zirconium sulfate, magnesium sulfophthalate, copper sulfophthalate, zirconium sulfophthalate, zirconium phthalate, zinc sulfate, zinc acetate, zinc chloride, calcium chloride, calcium bromide, magnesium sulfate, magnesium chloride, aluminum sulfophthalate, aluminum sulfoisophthalate, or combinations thereof.

15. The ink receiving medium/ink set according to claim 14 wherein the surfactant is selected from fluorochemical, silicone and hydrocarbon based surfactants, and combinations thereof.

16. A method of making an ink receiving medium comprising the steps of:

providing a macroporous substrate;  
applying a solution comprising surfactant and water-soluble multivalent metal salt  
onto a surface of said substrate; and  
removing solvent from said applied solution.

5

17. The method according to claim 16 wherein said surfactant is present in the solution  
in an amount of from about 0.01 to about 10 parts by weight.

10

18. The method according to claim 17 wherein said water-soluble multivalent metal  
salt is present in solution in an amount of from about 0.01 to about 50 parts by weight.

19. An imaged ink receiving medium comprising the ink receiving medium of claim 1  
having ink colorant fixed thereon.

15

20. The imaged receiving medium of claim 19 wherein said image is waterfast.

21. An ink receiving medium comprising a macroporous substrate having a pigment  
management system and an optional fluid management system wherein the pigment  
management system is a non-aqueous solvent soluble metal salt.

## MACROPOROUS INK RECEIVING MEDIA

### Abstract of the Disclosure

- 5     The invention provides an ink receiving medium comprising a macroporous substrate having a fluid management system and having a pigment management system in contact with surfaces of macropores of the substrate therein. In one embodiment, the pigment management system comprises water-soluble multivalent metal salt and the fluid management system comprises surfactant.

**DECLARATION, POWER OF ATTORNEY, AND PETITION**

I, a below named inventor, depose and say that: (1) my residence, citizenship, and mailing address are indicated below; (2) I have reviewed and understand the contents of attached specification, including the claims, as amended by any amendment specifically referred to herein, (3) I believe that the other below named inventors and I are the original, first, and joint inventors or discoverers of the invention or discovery in

**MACROPOROUS INK RECEIVING MEDIA**

described and claimed therein and for which a patent is sought; and (4) I hereby acknowledge my duty to disclose to the Patent and Trademark Office all information known to me to be material to the patentability as defined in Title 37, Code of Federal Regulations, §1.56.\*

I hereby appoint Gregory D. Allen (Reg. No. 35,048), Scott A. Bardell (Reg. No. 39,594), Carolyn A. Bates (Reg. No. 27,853), Stephen W. Bauer (Reg. No. 32,192), Dale A. Bjorkman (Reg. No. 33,084), Jennie G. Boeder (Reg. No. 28,952), William J. Bond (Reg. No. 32,400), Stephen W. Buckingham (Reg. No. 30,035), Paul W. Busse (Reg. No. 32,403), Gerald F. Chernivec (Reg. No. 26,537), James D. Christoff (Reg. No. 31,492), David R. Cleveland (Reg. No. 29,524), Philip Y. Dahl (Reg. No. 36,115), Charles L. Dennis II (Reg. No. 30,555), Janice L. Dowdall (Reg. No. 31,201), Lisa M. Fagan (Reg. No. 40,601), Darla P. Fonseca (Reg. No. 31,783), John A. Fortkort (Reg. No. 38,454), Matthew J. Goggin (Reg. No. 44,125), Melanie G. Gover (Reg. No. 41,793), Gary L. Griswold (Reg. No. 25,396), Doreen S. L. Gwin (Reg. No. 35,580), H. Sanders Gwin (Reg. No. 33,242), Michaele A. Hakamaki (Reg. No. 40,011), Karl G. Hanson (Reg. No. 32,900), Néstor F. Ho (Reg. No. 39,460), Jeffrey J. Hohenshell (Reg. No. 34,109), Robert W. Hoke (Reg. No. 29,226), John H. Hornickel (Reg. No. 29,393), MarySusan Howard (Reg. No. 38,729), Stephen C. Jensen (Reg. No. 35,207), Robert H. Jordan (Reg. No. 31,973), Harold C. Knecht III (Reg. No. 35,576), Kent S. Kokko (Reg. No. 33,931), Charles D. Levine (Reg. No. 32,477), Douglas B. Little (Reg. No. 28,439), Eloise J. Maki (Reg. No. 33,418), Lisa M. McGeehan (Reg. No. 41,185), Matthew B. McNutt (Reg. No. 39,766), Michelle M. Michel (Reg. No. 33,968), William D. Miller (Reg. No. 37,988), Peter L. Olson (Reg. No. 35,308), Daniel R. Pastirik (Reg. No. 33,025), David B. Patchett (Reg. No. 39,326), Carolyn V. Peters (Reg. No. 33,271), Scott R. Pribnow (Reg. No. 43,869), Terry K. Qualey (Reg. No. 25,148), Ted K. Ringsred (Reg. No. 35,658), James A. Rogers (Reg. No. 37,228), Daniel C. Schulte (Reg. No. 40,160), Steven E. Skolnick (Reg. No. 33,789), Robert W. Sprague (Reg. No. 30,497), Brian E. Szymanski (Reg. No. 39,523), James J. Trussell (Reg. No. 37,251), F. Andrew Ubel (Reg. No. 36,704), and Lucy C. Weiss (Reg. No. 32,834), my attorneys and/or agents with full powers (including the powers of appointment, substitution, and revocation) to prosecute this application and any division, continuation, continuation-in-part, reexamination, or reissue thereof, and to transact all business in the Patent and Trademark Office connected therewith; the mailing address and the telephone number of the above-mentioned attorneys and/or agents are

Attention: Scott A. Bardell  
Office of Intellectual Property Counsel  
3M Innovative Properties Company  
P.O. Box 33427  
St. Paul, Minnesota 55133-3427  
Telephone No. 651/736-6935

The undersigned petitioner declares further that all statements made herein of his own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

\*Title 37, Code of Federal Regulations, §1.56 is attached.

03716034 051630  
658150 "4201460

Wherefore, I pray for grant of Letters Patent for the invention or discovery described and claimed in the attached specification and we hereby subscribe our names to the foregoing specification and claims, declaration, power of attorney, and this petition, on the day set forth below.

Mark F. Schulz 5-18-99  
Date  
Mark F. Schulz  
Residence: Lake Elmo, Minnesota, U.S.A.  
Citizenship: U.S.A.  
Post Office P.O. Box 33427  
Address: St. Paul, Minnesota 55133-3427

Omar Farooq 5/18/99  
Date  
Omar Farooq  
Residence: Woodbury, Minnesota, U.S.A.  
Citizenship: U.S.A.  
Post Office P.O. Box 33427  
Address: St. Paul, Minnesota 55133-3427



**§1.56 Duty to disclose information material to patentability.**

(a) A patent by its very nature is affected with a public interest. The public interest is best served, and the most effective patent examination occurs when, at the time an application is being examined, the Office is aware of and evaluates the teachings of all information material to patentability. Each individual associated with the filing and prosecution of a patent application has a duty of candor and good faith in dealing with the Office, which includes a duty to disclose to the Office all information known to that individual to be material to patentability as defined in this section. The duty to disclose information exists with respect to each pending claim until the claim is cancelled or withdrawn from consideration, or the application becomes abandoned. Information material to the patentability of a claim that is cancelled or withdrawn from consideration need not be submitted if the information is not material to the patentability of any claim remaining under consideration in the application. There is no duty to submit information which is not material to the patentability of any existing claim. The duty to disclose all information known to be material to patentability is deemed to be satisfied if all information known to be material to patentability of any claim issued in a patent was cited by the Office or submitted to the Office in the manner prescribed by §§ 1.97(b)-(d) and 1.98. However, no patent will be granted on an application in connection with which fraud on the Office was practiced or attempted or the duty of disclosure was violated through bad faith or intentional misconduct. The Office encourages applicants to carefully examine:

- (1) prior art cited in search reports of a foreign patent office in a counterpart application, and
- (2) the closest information over which individuals associated with the filing or prosecution of a patent application believe any pending claim patentably defines, to make sure that any material information contained therein is disclosed to the Office.

(b) Under this section, information is material to patentability when it is not cumulative to information already of record or being made of record in the application, and

- (1) It establishes, by itself or in combination with other information, a prima facie case of unpatentability of a claim; or
- (2) It refutes, or is inconsistent with, a position the applicant takes in:
  - (i) Opposing an argument of unpatentability relied on by the Office, or
  - (ii) Asserting an argument of patentability.

A prima facie case of unpatentability is established when the information compels a conclusion that a claim is unpatentable under the preponderance of evidence, burden-of-proof standard, giving each term in the claim its broadest reasonable construction consistent with the specification, and before any consideration is given to evidence which may be submitted in an attempt to establish a contrary conclusion of patentability.

(c) Individuals associated with the filing or prosecution of a patent application within the meaning of this section are:

- (1) Each inventor named in the application;
- (2) Each attorney or agent who prepares or prosecutes the application; and
- (3) Every other person who is substantively involved in the preparation or prosecution of the application and who is associated with the inventor, with the assignee or with anyone to whom there is an obligation to assign the application.

(d) Individuals other than the attorney, agent or inventor may comply with this section by disclosing information to the attorney, agent, or inventor.

09314034 061830